



**Tabla : Espesores de Aislamiento (conservación de Calor)
LANA DE ROCA / LANA DE VIDRIO**

Diametro expresado en pulgadas	Temperatura °C											
	65 100	101 150	151 200	201 250	251 300	301 350	351 400	401 450	451 500	501 550	551 600	600 650
1/2 - 3/4	30	30	30	40	50	60	60	70	80	90	90	100
1 - 1 1/2	30	30	40	40	50	60	70	70	80	90	100	100
2	30	30	40	50	60	70	80	80	90	100	110	110
3	30	40	40	50	70	70	80	90	110	120	120	130
4	30	40	50	60	70	80	90	100	120	130	140	150
6	40	50	60	70	80	90	100	120	130	140	150	160
8	40	50	60	70	80	100	110	130	140	160	160	170
10	50	60	70	80	80	110	120	130	150	170	170	180
12	50	60	70		100	110	120	140	160	180	180	190
14	50	60	70		100	110	130	150	170	180	180	190
16	50	70	80		110	120	130	150	170	190	190	200
18	60	70	80		110	120	140	160	170	190	200	200
20	60	70	80		110	120	140	160	180	200	210	220
24 a >	60	70	90		120	130	150	170	190	200	220	230
Sup. Planas	70	70	90		120	130	150	180	190	210	220	230

Leyenda:		
Coquilla Lana de Vidrio	Coquilla Lana de Roca	
Manta Lana de Roca 70 Kg./ m3	Manta L. de Roca 100 Kg./m3	Manta Lana de Roca 125 Kg./m3

Jr. Chávez Tueros N° 1296, Chacra Ríos Sur Lima 1
Telef. : 425-9520 / 425-8130, Fax: 425-8130 / Nextel: 829-7173

gerdipac@gerdipac.com.pe

www.gerdipac.com.pe